



HSC 3300 (Solvent Cut Epoxy Resin)

Product Description	75% solution of Type 1 solid epoxy resin in xylene
	Suitable for formulation of solvent borne 2 component coatings with various curing agents like polyamines, polyamide, phenalkamines and various amine adducts
Features	<ul style="list-style-type: none">• Superior adhesion to metal & concrete,• superior resistance to water,• better anticorrosive properties,• good flexibility.
Applications	<ul style="list-style-type: none">• Anticorrosive primers for metals and concrete,• maintenance coatings,• modifier in stoving enamel

Product Specification

Properties	Units	Reference Standard	Value
Appearance	Visual	HTP-1	Clear to Yellowish
Color	Gardener	ASTM D 1544	<1
Viscosity* @ 25°C	mPas	ASTM D 2196	8000-13000
Epoxy Equivalent Weight**	gm/eq	ASTM D 1652	450-500
Density	g/ cc	ASTM D1475	1.1±0.05
Solid Content	%	ASTM D 1726	74-76

* 25% solution in Xylene

** Values for 100% Resin

HTP: HSCL Testing Procedure

Processing and Storage

Packing HSC 3300 available in bulk packing of MS epoxy coated drums. For handling and pumping the maximum temperature shall not exceed 35-40°C.

Safety & Handling Following instructions needs to be followed strictly. Keep working conditions clean. Allow fresh air in, if possible, provide ventilator. Avoid contact with human body directly, wear gloves and other personal protective equipment especially dust masks or respirators. Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water. In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling.

**Storage
Conditions**

HSC 3300 has a shelf-life of 12 months, if stored at room temperature free of moisture, in the original containers kept tightly closed at temperatures between 5-25°C. Container once opened should be tightly closed to avoid contamination by foreign materials.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Marketing & Sales Office**Hindusthan Speciality Chemicals
Limited**

65, Free Press House,
Free Press Journal Road,
Nariman Point, Mumbai – 400021
Tel: +91 22 61510960
Email- sales.hscl@hindusthan.co.in,

Works**Hindusthan Speciality Chemicals
Limited**

Plot No.:830,
GIDC, Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat – 393110, India
Website: www.hindusthanspeciality.com
