

Hardener HSC 8301

(Medium Curing Phenalkamines)

Product Description HSC 8301 is a light coloured, low viscosity phenalkamines form cashew nut shell liquid. It can able to cure modified and unmodified epoxy resin at room temperature as well as low temperatures up to 5°C. It is able to demonstrate good curing characteristic in presence of moisture and high humid conditions.

Features

- Good chemical resistance to acids and alkalis.
- excellent adhesion & film forming ability on variety of substrates.
- Moisture sensitive.

Applications

- Primers
- Paints
- Marine & Industrial coatings

Product Specifications

Properties	Units	Reference Standard	Value
Appearance	Visual	HTP-1	Yellow Brown liquid
Color	Gardener	ASTM D1544	14 Max
Viscosity @ 25°C	mPas	ASTM D2196	2000-5000
Amine value	Mg KOH/gm	ASTM D2073	300-350

Mix Properties	Units	Reference Standard	Value
Mix ratio with Epoxy Resin of EEW~185	Pbw	NA	100:67
Pot life (100gm) @ 25 °C	Minutes	ASTM D2471	50-65
Minimum Application Temperature	°C	NA	15

HTP: HSCL Testing Procedure
NA: Not Applicable

Processing and Storage

Packing HSC 8301 available in bulk packing of drums in packing size of 200 kg and 1000 kg IBC.

Safety & Handling Following instructions needs to be followed strictly.

- a. Keep working conditions clean. Allow fresh air in, if possible, provide ventilator.
- b. Avoid contact with human body directly, wear gloves and other personal protective equipment.
- c. Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water.
- d. In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling.

Storage Conditions

HSC 8301 should be stored in a cool and dry place, preferably in a sealed container and should not be exposed to direct sunlight. This product has a shelf-life of 1 year, if stored in its original container between 18°C and 25°C away from humidity and excessive heat.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Marketing & Sales Office

Hindusthan Speciality Chemicals Limited

65, Free Press House,
Free Press Journal Road,
Nariman Point, Mumbai – 400021
Tel: +91 22 61510960
Email- sales.hscl@hindusthan.co.in

Works

Hindusthan Speciality Chemicals Limited

Plot No.:830, GIDC,
Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat – 393110, India
Website: www.hindusthanspeciality.com
