

Hardener HSC 9222

(Medium viscous modified amine curing agent)

Product Description HSC 9222 is medium viscous modified amine curing agent. It is used in combination with unmodified/modified liquid epoxy resins for adhesives & lamination applications. It offers medium pot life, good wetting ability and high viscosity.

Features

- Medium viscosity transparent clear system,
- Moderate setting time

Applications

- Imitation jewellery
- Glass like transparent coating

Product Specifications

Properties	Units	Reference Standard	Value
Appearance	Visual	HTP-1	Clear liquid
Color	Gardener	ASTM D 1544	Max 1
Viscosity at 25 °C	mPas	ASTM D 2196	5000-8000

Mix Properties	Units	Reference Standard	Value
Mix ratio with Epoxy Resin of EEW~185	Pbw	NA	100:50
Mix viscosity at 25 °C	mPas	ASTM D2196	8000-12000
Pot life (100 g) at 25 °C	Minutes	ASTM D2471	30-40
Cure Schedule	NA	NA	24h RT + 7 day full cure

HTP : HSCL Testing Procedure

NA : Not Applicable

Processing and Storage

Packaging HSC 9222 available in bulk packing of drums and container in packing size of 5 kg and 0.25 kg bottles.

Safety & Handling Following instructions needs to be followed strictly.
 Keep working conditions clean. Allow fresh air in, if possible, provide ventilator. Avoid contact with human body directly, wear gloves and other personal protective equipment especially dust masks or respirators.
 Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water.

In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling.

Storage Conditions

HSC 9222 should be stored at room temperature free of moisture, in the original containers kept tightly closed at temperatures between 5-35°C. Container once opened should be tightly closed to avoid contamination by foreign materials. The shelf life for hardener HSC 9222 is 12 months from date of manufacturing.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Marketing & Sales Office

Hindusthan Speciality Chemicals Limited

65, Free Press House,
Free Press Journal Road,
Nariman Point, Mumbai – 400021
Tel: +91 22 61510960
Email- sales.hsclathindusthan.co.in

Works

Hindusthan Speciality Chemicals Limited

Plot No.:830, GIDC,
Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat – 393110, India
Website: www.hindusthanspeciality.com
