



HSC 4153 **(Reactive Diluent)**

Product Description

HSC 4153 is aromatic functional reactive epoxy reactive diluent based on benzyl alcohol. It has low toxicity compared to phenyl glycidyl ether. .

Key Properties

- It assists in reducing the viscosity of basic liquid resin and has good dilution efficiency.
- It has better mechanical & heat resistance property properties compared to long chain aliphatic alcohol-based epoxy reactive diluents used for coatings.
- The aromatic character helps to increase the chemical resistance and gloss of the final coating.

Applications

- Adhesives and abrasive application
- Coatings - Primers and Top coat for flooring and related applications

Product Specifications

Properties	Units	Reference Standard	Value
Appearance	Visual	HTP-1	Slight Yellow Liquid
Color	Gardener	ASTM D 1544	Max 0.5
Viscosity @ 25°C	mPas	ASTM D 2196	5-10
Epoxy Equivalent Weight	gm/eq	ASTM D 1652	200-220
HTP: HSCL Testing Procedure			

Processing and Storage

Packing

HSC 4153 is available in bulk packing of 220 Kg HDPE drums.

Safety & Handling

Following instructions needs to be followed strictly. Keep working conditions clean. Allow fresh air in, if possible, provide ventilator. Avoid contact with human body directly, wear gloves and other personal protective equipment especially dust masks or respirators. Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water. In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling

**Storage
Conditions**

HSC 4153 should be stored at room temperature free of moisture, in the original containers kept tightly closed at temperatures between 5-35°C. Container once opened should be tightly closed to avoid contamination by foreign materials. The shelf life of the material is 24 months.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Marketing & Sales Office**Hindusthan Speciality Chemicals
Limited**

65, Free Press House,
Free Press Journal Road,
Nariman Point, Mumbai – 400021
Tel: +91 22 61510960
Email- sales.hscl@hindusthan.co.in,

Works**Hindusthan Speciality Chemicals
Limited**

Plot No.:830,
GIDC, Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat – 393110, India
Website: www.hindusthanspeciality.com
