



HSC 4560 **(Reactive Diluent)**

Product Description

HSC 4560 is cycloaliphatic di-functional epoxy reactive diluent based on cyclohexanedimethanol. It is compatible in all concentrations to help reduce the viscosity of the basic liquid resin. It is used to improve electrical insulation, UV and weather resistance.

Features

- Excellent weather resistance
- Very good mechanical and electrical properties
- Good thermal shock resistance
- Very good resistance to erosion by UV radiation
- Decreases the viscosity of epoxy resin

Applications

- Outdoor coatings, anti-corrosive preparations
- Outdoor floorings toppings and floor coats
- Electrical insulating parts like bushings
- Post type insulators for medium voltage out-door applications

Product Specifications

Properties	Units	Reference Standard	Value
Appearance	Visual	HTP-1	Clear Liquid
Color	Gardener	ASTM D 1544	Max 1
Viscosity @ 25°C	mPas	ASTM D 2196	40-80
Epoxy Equivalent Weight	gm/eq	ASTM D 1652	150-170
Hydrolysable chlorine	%	ASTM D 1726	Max 0.1
HTP: HSCL Testing Procedure			

Processing and Storage

Packing

HSC 4560 is available in bulk packing of 220 Kg HDPE drums. Other packs are available on request.

Safety & Handling

Following instructions needs to be followed strictly. Keep working conditions clean. Allow fresh air in, if possible, provide ventilator. Avoid contact with human body directly, wear gloves and other personal protective equipment especially dust masks or respirators. Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water. In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling.

**Storage
Conditions**

HSC 4560 should be stored at room temperature free of moisture, in the original containers kept tightly closed at temperatures between 5-40°C. Container once opened should be tightly closed to avoid contamination by foreign materials. The shelf life of the resin is 24 months.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Marketing & Sales Office

**Hindusthan Speciality Chemicals
Limited**

65, Free Press House,
Free Press Journal Road,
Nariman Point, Mumbai – 400021
Tel: +91 22 61510960
Email- sales.hscl@hindusthan.co.in,

Works

**Hindusthan Speciality Chemicals
Limited**

Plot No.:830,
GIDC, Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat – 393110, India
Website: www.hindusthanspeciality.com
